



Chemical Materials Division

Kenospheres WS-125

Product Name: Kenospheres - White Series - 125µm - (Alumino-Silicate Hollow Ceramic Microspheres)

Introduction

Kenospheres White Series 125µm (Hollow Ceramic Microspheres) serve as high-performance additives derived from alumino-silicate material. These hollow ceramic microspheres are byproducts of coal combustion and are designed to offer enhanced thermal insulation and buoyancy across a range of demanding applications.

They are particularly effective in industries such as paints and coatings, automotive composites, and construction materials. Kenospheres contribute to weight reduction and offer additional benefits like noise and vibration dampening, reduced thermal expansion, and overall cost savings. They are utilized in a multitude of applications across diverse markets, including aerospace, marine, and thermal insulation materials.

The spherical shape of Kenospheres allows for higher filler loading and superior flowability, thereby elevating the overall performance of your products. Composed of a silica-alumina blend, these microspheres are water-resistant and compatible with a wide range of resins. Their non-combustible and non-porous nature further enhances their versatility, positioning them as a premium alternative to traditional fillers like silica and calcium carbonate.

Material Description (Not for specification purposes.)

Property	Kenospheres™ WS-125
Shape	Hollow spheres with thin walls
Composition	Alumino-Silicate Ceramic Material
Color, unaided eye	White

Typical Physical Properties (Not for specification purposes.)

Property	Kenospheres™ WS-125
Bulk weight (g/cm ³)	0.36 - 0.46
Specific gravity (g/cm ³)	0.75 - 0.92
Packing factor (bulk density to true particle density)	60%
Average diameter (microns)	88
Softening point (°C)	1200
Melting point (°C)	1525 - 1650
Moisture content (%)	< 0.3
Sinker (%)	< 12
pH	7.0 - 9.9

Typical Chemical Composition by Element (Not for specification purposes.)

Element	Typical Composition	Range
Al ₂ O ₃	36.20%	34 - 38%
SiO ₂	57.00%	55 - 60%
Fe ₂ O ₃	1.60%	1.0 - 3.0%
MnO	0.20%	0.1 - 0.5%
MgO	0.60%	0.5 - 1.0%
Na ₂ O	0.40%	0.4 - 0.9%
TiO ₂	1.10%	0.8 - 2.0%
CaO	1.00%	1.0 - 2.0%

Typical Particle Size Distribution (Not for specification purposes.)

Particle Size Range	Typical Distribution	Maximum
> 150µm	0%	0%
125 - 150µm	0%	2%
63 - 125µm	90%	95%
< 63µm	10%	20%

*The data provided represents the standard characteristics of the product, based on our most reliable information. This test data is generated through documented procedures and test methods.

Formulating Information

Flow Properties

Kenospheres WS-125 maintain their free-flowing nature for an extended period, ensuring easy mixing and even distribution. Proper storage in the original, unopened container as per recommended conditions will preserve these properties for years.

Microsphere Breakage

While Kenospheres WS-125 are designed for high strength-to-weight ratios, breakage can occur under severe processing conditions. To minimize this, it's advisable to limit exposure to high-shear processes and point contact shear, such as gear pumps and 3-roll mills.

For extrusion processes, the material should be added downstream of the feed hopper via a side stuffer or top feeder, similar to the addition of glass fibers. For any concerns regarding breakage or processing, please contact our technical service team for assistance.

For additional technical information on Kenospheres, visit our website <https://kenospheres.com/> or contact our customer service team. email: support@kenospheres.com

Packaging

Kenospheres are available in the following packaging sizes to suit various industrial needs:

Big bags: 500 kg with a plastic liner (2 bags stacked per pallet).

Paper bags: 20 kg net, on pallets.

Product Storage, Handling & Safety

Storage

Optimal storage conditions for Kenospheres include keeping them in unopened bags within a dry, temperature-controlled environment.

Prolonged exposure to high humidity or conditions prone to condensation may result in "caking" of the microspheres. To minimize caking and maximize storage life, consider the following:

- Promptly reseal opened bags after use.
- If the bag is damaged during shipping or handling, seal the hole immediately or transfer the contents to an undamaged bag.
- During hot and/or humid months, store bags in the driest, coolest space available.

-If controlled storage conditions are not available, maintain a minimal inventory and operate on a first-in, first-out basis.

Handling

Due to the lightweight and small particle size of Kenospheres, dusting may occur during handling and processing. To minimize dusting, consider:

- Not opening Kenospheres packages until ready for use.
- Using local exhaust ventilation near the opening to capture airborne particles.
- Employing a suction "wand" for transferring to a closed mixing tank, or using dust collection equipment if a closed tank is not available.
- Utilizing static eliminators to prevent static buildup.

Safety

For worker protection, consider:

- Wearing safety glasses with side shields.
- Using an air-purifying respirator suitable for particulates after conducting an optional exposure assessment.
- Employing local exhaust ventilation/dust collection in the work area.
- Refer to the Kenospheres Safety Data Sheet for additional safety information.



Kenospheres.

Kenospheres is a registered trademark of InnovaCorp LTD. Used under license by InnovaCorp subsidiaries and affiliates, as well as licensed third-party companies. Please recycle. Printed in Cyprus.

©InnovaCorp LTD 2023.

All rights reserved.

Issued: 2/23.



InnovaCorp.

InnovaCorp LTD
Chemical Materials Division
Kon. Kavafi 11, 7562, Larnaca, Cyprus
Web: www.innovative-corporation.com/

Warranty, Limited Remedy, and Disclaimer: Numerous factors beyond InnovaCorp LTD's control and uniquely within the user's knowledge and control can impact the use and performance of an InnovaCorp LTD product in a specific application. The user is solely responsible for evaluating the Kenospheres product and determining its suitability for a particular purpose and method of application. The user is also solely responsible for evaluating third-party intellectual property rights and ensuring that the use of InnovaCorp LTD products does not infringe upon them. Unless explicitly stated otherwise in the relevant product literature or packaging insert, InnovaCorp LTD warrants that each product meets the applicable InnovaCorp LTD product specification at the time of shipment. INNOVACORP LTD MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If the InnovaCorp LTD product fails to conform to this warranty, the sole and exclusive remedy is, at InnovaCorp LTD's option, replacement of the product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, InnovaCorp LTD will not be liable for any loss or damages arising from the Kenospheres product, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including warranty, contract, negligence, or strict liability.

Technical Information: Technical information, recommendations, and other statements contained in this document or provided by InnovaCorp LTD personnel are based on tests or experience that InnovaCorp LTD believes to be reliable. However, the accuracy or completeness of such information is not guaranteed. This information is intended for individuals with the knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any InnovaCorp LTD or third-party intellectual property rights is granted or implied with this information.